

TECHNICAL DATA SHEET

PRODUCT	
60s SILICA SAND	Added to a clay body they help glaze fit and make the body more refractory.

TYPICAL SIEVE ANALYSIS (MEAN VALUES. THESE DO NOT REPRESENT A SPECIFICATION.)	
710	0.1%
500	1.7%
355	9.1%
250	28.0%
180	43.0%
125	15.8%
90	2.0%
63	0.3%
<63	0.0%
Typical AFS	58.0%
Nominal AFS	60.0%
Nominal AGS	251%

PRODUCT SIZE
The products are available in Paper Bags (25kg).