

Technical Data Sheet

ES950 (Airdrying) Earthstone



Hand Building



Modelling



Firing Range: Airdrying



Colour: Grey



Texture: Smooth Textured



Bag Size: 12.5kg



Chemical Analysis %

Chemical	Percentage
SiO ₂	64.30
TiO ₂	1.30
Al ₂ O ₃	22.90
Fe ₂ O ₃	1.11
P ₂ O ₅	<>
CaO	0.18
MgO	0.39
K ₂ O	2.20
Na ₂ O	0.27

% Total Contraction

1100°C	n/a
1200°C	n/a

Thermal Expansion

500°C	n/a
600°C	n/a

This technical information is only a guide, established from the characterisation and analysis of representative samples, and from routine production averages.

Product characteristics are subject to modifications.

Valentine Clays

MANUFACTURED IN THE HEART OF THE POTTERIES