

# TECHNICAL DATA SHEET

PRODUCT	
<b>FFF K7 60 FELDSPAR</b>	A blend of Soda and Potash Feldspars used as a fluxing agent in both clay and glaze preparation.

PARTICLE SIZE ANALYSIS AND PROPERTIES (MEAN VALUES. THESE DO NOT REPRESENT A SPECIFICATION.)	
Sieve Size $\mu\text{m}$	Typical % Retained
< 32 $\mu$	95.0%
< 20 $\mu$	79.0%
< 10 $\mu$	42.9%
< 5 $\mu$	28.0%
< 2 $\mu$	11.3%
< 1 $\mu$	5.0%

CHEMICAL ANALYSIS (MEAN VALUES. THESE DO NOT REPRESENT A SPECIFICATION.)		
Silicon Oxide	SiO <sub>2</sub>	67.3
Aluminium Oxide	Al <sub>2</sub> O <sub>3</sub>	19.1
Iron Oxide	Fe <sub>2</sub> O <sub>3</sub>	0.1
Calcium Oxide	CaO	1.0
Sodium Oxide	Na <sub>2</sub> O	4.9
Potassium Oxide	K <sub>2</sub> O	7.2
Magnesium Oxide	MgO	<0.03%

## Product Availability

The products are available in Paper Bags (25kg) or (40kg)