

Technical Data Sheet

LoStone: Frost Casting Slip



Casting



Firing Range: 1080-1240°C

Cone 03 to Cone 7 (maximum)



Colour: Off-white



Texture: Smooth

Fired at

1240°C

1220°C

1200°C

1180°C


1160°C

1140°C

1120°C

1100°C

1080°C



Chemical Analysis %	
Chemical	%
SiO ₂	64.93
TiO ₂	1.06
Al ₂ O ₃	21.95
Fe ₂ O ₃	0.61
CaO	0.42
MgO	0.24
K ₂ O	3.35
Na ₂ O	1.84
LOI	5.85

Thermal Expansion	
% at 500°C	0.351
Coefficient of Expansion C.O.E (x 10 ⁻⁶)	7.3

This technical information is only a guide, established from the characterisation and analysis of representative samples, and from routine production averages. Product characteristics are subject to modifications.