Technical Data Sheet

HT Special Stoneware





Throwing

Modelling



Firing Range: 1120-1280°C



Colour: Buff



Texture: Smooth Textured



Bag Size: 12.5kg

| Fired at | |
|----------|--|
| 1300°C | |
| 1280°C | |
| 1260°C | |
| 1240°C | |
| 1220°C | |
| 1200°C | |
| 1180°C | |
| 1160°C | |
| 1140°C | |

| Chemical Analysis % | | |
|--------------------------------|------------|--|
| Chemical | Percentage | |
| SiO ₂ | 66.10 | |
| TiO ₂ | 1.03 | |
| AL ₂ O ₃ | 20.70 | |
| Fe ₂ O ₃ | 2.04 | |
| P ₂ O ₅ | 0.06 | |
| CaO | 0.21 | |
| MgO | 0.63 | |
| K ₂ O | 2.02 | |
| Na₂O | 0.13 | |

| % Total Contraction | |
|---------------------|-------|
| 1100°C | Х |
| 1200°C | 1211% |
| | % |

| Thermal Expansion | |
|-------------------|--|
| 0.252 | |
| 0.350 | |
| | |

This technical information is only a guide, established from the characterisation and analysis of representative samples, and from routine production averages.

Product characteristics are subject to modifications.



