

Technical Data Sheet

Luna Fleck Stoneware



Throwing



Hand Building



Firing Range: 1120-1260°C



Colour: Buff



Texture: Smooth Textured



Bag Size: 12.5kg

Fired at

1300°C

1280°C

1260°C

1240°C

1220°C

1200°C

1180°C

1160°C

1140°C



Chemical Analysis %


Chemical	Percentage
SiO ₂	60.13
TiO ₂	1.18
Al ₂ O ₃	24.47
Fe ₂ O ₃	2.70
P ₂ O ₅	0.04
CaO	0.35
MgO	0.78
K ₂ O	1.91
Na ₂ O	0.18
LOI	8.26

% Thermal Expansion

500°C	0.256
600°C	0.348

% Total Contraction

1100°C	X
1200°C	13.00



This technical information is only a guide, established from the characterisation and analysis of representative samples, and from routine production averages.

Product characteristics are subject to modifications.