

Technical Data Sheet

V9A Stoneware



Throwing



Modelling



Casting



Firing Range: 1120-1280°C



Colour: Buff



Texture: Smooth



Bag Size: 12.5kg

Fired at

1300°C

1280°C

1260°C

1240°C

1220°C

1200°C

1180°C

1160°C

1140°C



Chemical Analysis %	
Chemical	Percentage
SiO ₂	61.30
TiO ₂	1.20
Al ₂ O ₃	24.41
Fe ₂ O ₃	2.38
P ₂ O ₅	0.04
CaO	0.22
MgO	0.64
K ₂ O	1.91
Na ₂ O	0.10

% Total Contraction	
1100°C	X
1200°C	13%

Thermal Expansion	
500°C	0.268
600°C	0.369

This technical information is only a guide, established from the characterisation and analysis of representative samples, and from routine production averages.

Product characteristics are subject to modifications.

